



DATA SHEET

Standard MgO Chrome Brick					
Item NO		RT-MGe-8	RT-MGe-12	RT-MGe-16	RT-MGe-20
Physical Property:					
Bulk Density(g/cm3)	≥	2.9	2.95	3	3.05
Apparent Porosity(%)	≤	21	21	22	22
Cold Crushing Strength(MPa)	≥	35	30	25	25
Refractoriness Under Load(T0.6 °C)	≥	1530	1550	1550	1550
Chemical Analysis(%)					
MgO	≥	65	55	45	40
Cr2O3	≥	8	12	16	20
Note:All data are average values obtained at samples for laboratory purposes.					